


# BISPHENOL-A



TRADEASIA

## General Information

Chemical Formula	$(\text{CH}_3)_2\text{C}(\text{C}_6\text{H}_4\text{OH})_2$	
Synonym	BPA	
Origin	Taiwan	
H.S. Code	2907.23	
CAS No.	80-05-7	
Molecular Weight	228.29 g/mole	

## Application

Plastics Industry	It is used to manufacture polycarbonate plastic which is used in a wide variety of common products.
Epoxy resins	It is used to manufacture epoxy resin which is commonly used to make protective coatings.
Others	It is used as an antioxidant in some plasticizers and polymerization of inhibitor in PVC production.

## Specification

Property	Units	Value
Appearance		White, Bead, Prill
Purity	%	99.8 (min)
Melting Point	°C	156.5 (min)
O,P-BPA Content	ppm	500 (max)
Phenol	ppm	100 (max)
Moisture	ppm	1000 (max)
Iron	ppm	1 (max)
Molten Color	APHA	25(max)
Ash	ppm	20 (max)

## Packaging

- 640 @ 25 kg PP/PE Bag, 16 MT / 20'FCL (without pallet)
- 480 @ 25 kg PP/PE Bag, 12 MT / 20'FCL (with pallet)

Tradeasia International Pte Ltd  
133 Cecil Street # 12-03 Keck Seng Tower  
Singapore 069535  
Republic Of Singapore  
Tel : +65 6227 6365  
Fax : +65 6225 6286  
Email : contact@chemtradeasia.com